

### Typical Properties of DAKREN™ series

	Unit	Method	1035X	1035HX	1035UHX	1040	1030L
Appearance			White Powder				
Chlorine Content	wt%	GB/T9872	34	34	34	38	28
Specific Gravity	g/cm <sup>3</sup>	JIS K-0061	1.19	1.19	1.19	1.26	1.15
Volatile Matter	wt%	GB/T2914	Max 0.5	Max 0.5	Max 0.5	Max 0.5	Max 0.5
Hardness	Shore A	GB/T531	55	55	55	55	62
Tensile Strength	MPa	GB/T528	12	12	12	7	12
Elongation	%	GB/T528	800	800	800	600	850
Mooney Viscosity	ML1+4 at 121°C	GB/T1232	68	80	-	70	60
Applications			Rubber	Rubber PVC	PVC Rubber	Rubber	Rubber



GENERAL TRADERS IMPORTERS & EXPORTERS  
Sanyo Corporation of America

500 Fifth Avenue Suite#3620 New York NY 10110, USA  
TEL : 212-221-7890 FAX : 212-221-7828  
info@sanyocorpusa.com  
www.sanyocorpusa.com