



## Synthetic Cryolite (Sodium hexa fluoro aluminate)

### Components

$\text{Na}_3\text{AlF}_6$

### CAS NO.

15096-52-3

### Specification

$\text{Na}_3\text{AlF}_6$ :96.0% min.

$\text{H}_2\text{O}$ :0.2% max.

F:52.5% min.

Na:32~33%

Al:12~13%

### Packing

1) 25kg

or 50kg net weight

Multiple paper bags

With inner PE bags

2) IMT big bags

\* Mesh size

Grade3 : +100mesh 0%  
+200mesh 5%max.  
+325mesh 20%max.  
Grade6: +200mesh Tr.  
+325mesh 3%max.

### Applications

Aluminum smelting

Fluxes for steel

Resin Abrasives

Insecticide

Milk glass

Sanyo Corporation of America  
500 Fifth Avenue Suite#3620  
New York NY 10110, USA  
TEL : 212-221-7890  
FAX : 212-221-7828

<http://www.sanyocorpusa.com/en/index.html>

The information contained in the technical data sheet is, to the best of our knowledge, true and accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe any patent.